Do not enter. -WA

Appln. No. 10/561,913

Amdt. dated April 22, 2011

Reply to Notice of Allowance of January 27, 2011

## Amendments to the Abstract

Please replace the originally filed abstract with the following amended abstract:

The object of the present invention is to offer a A can that features superior resistance against puncture under higher puncture strength, and superior resistance against flange cracking.

The resin-coated aluminum seamless can body of the present invention features superior resistance against cracks in the can wall during distribution, and resistance against flange cracking, wherein the inner and/or outer surface of the can of the aluminum seamless can 10 is coated with a layer of thermo-plastic resin, the thickness of the thermo-plastic resin layers of the inner surface and the outer surface is a total of  $2-50 \mu m$ , with a minimum thickness of the aluminum plate of the side wall of the can  $0.110 \ mm$  or less, and the tensile stress at break measured for the aluminum plate that is removed from the thermo-plastic resin of the side wall of the can in the direction of the circumference of the can, is  $450 \ MPa$  or less, the product of the minimum thickness of a plate of the side wall of the can including the thermo-plastic resin <t><t

(mm), and the tensile stress measured of the side wall of the can including the thermo-plastic resin in the direction of height of the cans (MPa), is <t $\le$ s $\ge$ 30.

The thermo-plastic resin layer is a thermo-plastic polyester resin layer having oriented crystals, wherein the heat of fusion of the polyester resin layer is not less than 15 l/g.